



Size Board

| | |
|----------------------------|----------------------|
| LENGTH | 1860 mm |
| WIDTH | 189 mm |
| TOTAL THICKNESS | 15 mm |
| THICKNESS TOP LAYER | 4.00 mm |
| PLANK QUANTITY | Min. 7 Pl. x 1860 mm |

Size Pack

| | |
|---------------------------|--------------------|
| PACK LENGTH | 1870mm |
| PACK WIDTH | 200mm |
| PACK THICKNESS | 130mm |
| PACK WEIGHT | 25.00kg |
| LAYERS/PACK | 8 |
| M²/PACK | 2.81m ² |

Size Pallet

| | |
|-----------------------------|----------------------|
| LENGTH PALLET | 1890mm |
| WIDTH PALLET | 1000mm |
| HEIGHT PALLET | 1160mm |
| WEIGHT PALLET | 1015.00kg |
| PACKS/PALLET | 40 |
| M²/PALLET | 112.40m ² |

Characteristics

Top layer

| | |
|----------------------------|--------------------------|
| WOOD SPECIES | Oak |
| LATIN NAME | Quercus Mongolica |
| GRADE | ABC |
| CONSTRUCTION | 3-layer |
| THICKNESS TOP LAYER | 4.00 mm |
| STRIPS | 1 strip |
| CUTTING METHOD | Sawn veneer |
| BEVEL | Two long sides (0,75 mm) |
| COLOUR FINISH | Smoked |
| SURFACE STRUCTURE | Smooth |

Composition of the support

| | |
|--------------------------------|-----------------------------|
| SUPPORT TYPE | Poplar support and backing |
| WOOD SPECIES SUPPORT | Poplar |
| SUPPORT CONSTRUCTION | 2-layer (Support, balancer) |
| TOTAL THICKNESS SUPPORT | 11.00mm |
| ADHESION | Crosswise (Casco) |

Installation

SYSTEM

Tongue and groove system



APPLICATIONS

- Light household use
- Moderate commercial use
- Normal commercial use
- Normal household use
- Intensive commercial use

UNDERFLOOR HEATING

Yes

HERSCHUURBAAR

Resandable

Certification

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

Technical specifications

- Hardness: N / mm² (Birrell Hardness) 3.40
- Thermal conductivity: λ 14, 00 (W / (mk)) R = 0.11 m² K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)